

WHAT IS CLAIMED IS:

1. A resin composition comprising a polyolefin resin (A), a metal soap (B) of the following formula (1), which is obtained
5 by a heat reaction by a dry direct method of one or more kinds of aliphatic monocarboxylic acid having 12 to 30 carbon atoms and an oxide or hydroxide of group II metal of the periodic table, a saponified product (C) of an ethylene-vinyl acetate copolymer having an ethylene content of 70-95 mol% and a
10 saponification degree of a vinyl acetate component of not less than 85 mol%, and a hydrotalcite compound and/or a hydrotalcite solid solution (D):



wherein α is a number of 0.1-1.0, M is a divalent metal of
15 group II of the periodic table, and R is a saturated or unsaturated alkyl group having 11 to 29 carbon atoms.

2. The resin composition of claim 1, wherein the content of the metal soap (B) in the resin composition is 0.005-20 wt%.

20 3. The resin composition of claim 1, wherein the content ratio of the polyolefin resin (A) and the saponified product of an ethylene-vinyl acetate copolymer (C), (A/C), is 95/5-30/70 (weight ratio).

25 4. The resin composition of claim 2, wherein the content ratio of the polyolefin resin (A) and the saponified product of an ethylene-vinyl acetate copolymer (C), (A/C), is 95/5-30/70 (weight ratio).

30 5. The resin composition of claim 1, which is added to a collected material of a laminate comprising a layer containing a saponified product of an ethylene-vinyl acetate copolymer

having an ethylene content of 20-65 mol% and a saponification degree of a vinyl acetate component of not less than 90 mol%.

6. The resin composition of claim 2, which is added to a
5 collected material of a laminate comprising a layer containing a saponified product of an ethylene-vinyl acetate copolymer having an ethylene content of 20-65 mol% and a saponification degree of a vinyl acetate component of not less than 90 mol%.

10 7. The resin composition of claim 3, which is added to a collected material of a laminate comprising a layer containing a saponified product of an ethylene-vinyl acetate copolymer having an ethylene content of 20-65 mol% and a saponification degree of a vinyl acetate component of not less than 90 mol%.

15

8. The resin composition of claim 4, which is added to a collected material of a laminate comprising a layer containing a saponified product of an ethylene-vinyl acetate copolymer having an ethylene content of 20-65 mol% and a saponification
20 degree of a vinyl acetate component of not less than 90 mol%.